Deep Cycle SLA Battery

DC SERIES

bosfa

DC (Deep cycle) Series batteries are designed for deep discharge application, with special chemical formula for plates active paste material, slightly stronger electrolyte and low temperature design, which can withstand repeated deep cyclic application, such as Solar Energy System, Golf Trolley, Electric

VRLA Battery

Application

- Solar Energy System
- Golf Cars and Buggies
- Electric Powered Vehicles
- Wheel Chairs

- Power Tools
- Electric Powered Toys
- Control System
- Vacuum Cleaners
- Medical Equipments

General Features


- Sealed and maintenance free operation.
- Non-Spillable construction design.
- ABS containers and covers(UL94HB, UL94V-0) optional.
- Safety valve installation for explosion proof.
- High quality and high reliability.
- Exceptional deep discharge recovery performance.
- Low self discharge characteristic.
- Flexibility design for multiple install positions.

Construction


•	Componer	nt	.Raw material
•	Positive		Lead dioxide
•	Negative		.Lead
•	Container		.ABS
•	Cover		.ABS


- SealantEpoxy Resin
- Safety valveEPDR • TerminalCopper
- SeparatorFibre glass
- ElectrolyteSulfuric acid






Terminal Dimensions








Battery Model	DC 6-120					
Designed Cycle Life	> 350 cycles @ -0.5CA to 9.6V					
Capacity(25°C)	20HR(6.1A,1.75V)	10HR(12A,1.75V)	5HR(20.4A,1.75V)	1HR(72A,1.75V)		
Capacity(25 C)	122AH	122AH 120AH		72AH		
Dimensions	Length	Width	Height	Total Height		
Dimensions	194mm(7.64inch)	170mm(6.69inch)	207mm(8.15inch)	210mm(8.27inch)		
Approx. Weight	16Kg (35.28 lbs)					
Internal Resistance	Full charged at 25°C: 0.005 Ohm					
Self Discharge	3% of capacity declined per month at (25°C)					
Capacity Affected	40°C	25°C	0°C	-15°C		
by Temp.(20HR)	102%	100%	85%	65%		
Chargo Voltago(25°C)	Cycle	e use	Float use			
Charge Voltage(25°C)	7.2-7.5V(-15mV/ °C),	max. Current: 36A	6.8-6.9V(-10mV/ °C)			

bosfa

Deep Cycle SLA Battery



Constant current discharge ratings-amperes at 25°C

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	3HR	5HR	10HR	20HR
1.60V	526	327	247	151	86.7	38.1	23.3	12.7	6.85
1.67V	494	310	237	144	85.6	36.6	22.8	12.5	6.61
1.70V	452	299	232	131	83.0	34.2	22.3	12.5	6.50
1.75V	443	290	224	124	79.1	33.0	21.8	12.4	6.33
1.80V	397	277	204	115	74.0	31.7	20.5	12.2	6.16
1.85V	350	264	183	106	69.0	30.6	19.2	12.0	6.03

Constant power discharge ratings-watts at 25°C

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	3HR	5HR	10HR	20HR
1.60V	923	591	451	271	156	67.5	39.3	26.0	13.7
1.67V	890	576	445	266	156	65.4	39.1	25.9	13.2
1.70V	838	570	441	249	153	62.5	38.6	25.4	13.0
1.75V	844	568	438	241	150	61.0	38.3	25.1	12.7
1.80V	772	560	406	230	141	59.2	37.1	24.7	12.4
1.85V	700	531	368	215	133	57.4	35.9	24.3	12.2





COPYRIGHT BOSFA INDUSTRIAL BATTERY CO.,LTD.